


1K All Plastics Primer

FOR PROFESSIONAL USE ONLY

Description


Quick drying, one-pack adhesion primer for plastic car body parts.




Ready to spray



Shake thoroughly before use




Application distance
12-18 cm



1 coat



Invert aerosol and depress nozzle after use



Recoatable after:

20 minutes at 20°C

Recoat within:

24 hours at 20°C



Recoatable with all Sikkens primer fillers/surfacers and topcoats



Use suitable respiratory protection

Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information



1K All Plastics Primer

FOR PROFESSIONAL USE ONLY

Description

Quick drying, one-pack adhesion primer for plastic car body parts.

Suitable substrates

All plastic car body parts available to date, with the exception of those made of pure PE (polyethylene).

1K All Plastics Primer is specially designed for application to soft polyurethane plastic car parts.
 Do **not** apply 1K All Plastics Primer to plastic parts that are pretreated with OEM primer.

Products and additives

Aerosol 1K All Plastics Primer

Basic raw materials

Polyolefine resins

Surface preparation



Pre-clean the surface with warm water and detergent, rinse sufficiently with clean water.
 Remove surface contamination using M700, Anti Static Degreaser or M850.



Untreated plastic part

Thoroughly abrade all surfaces using Sikkens Plastic Prep in combination with water.
 Use a 3M VFN (Purple) abrasive pad on hard plastics and a 3M UFN (Grey) abrasive pad in case of a flexible/soft plastic part, rinse sufficiently with clean water after use.

For specific plastic part preparation procedures and detailed surface preparation see TDS S8.06.03



Painted plastic part

Sanding; final dry sanding steps; P220 - P320
 For spot repair sand the featheredge with P400



Remove surface contamination using M700, Anti Static Degreaser or M850.
 Where bodyfiller is exposed, avoid contact with water (e.g. waterborne degreaser).




1K All Plastics Primer

FOR PROFESSIONAL USE ONLY

Application



Hold aerosol approximately 12-18 cm from the panel and apply 1 even coat over untreated plastic substrates.




After application, invert aerosol and depress the nozzle for 2-3 seconds. This allows the propellant to clean the nozzle sufficiently for further use.

Film thickness

By using the recommended application: 1-4 µm

Recoat time



Allow for a minimum of 20 minutes flash-off time at 20°C before recoating. Apply the primer fillers/surfacers or topcoat within 24 hours at 20°C

Should this maximum time be exceeded, abrade the surface with 3M UFN (Grey) before recoating once again with one full coat of 1K All Plastics Primer.

Recoatable with



All Sikkens primers/fillers, surfacers and topcoats.

Theoretical Coverage

By using the recommended application, the theoretical material usage is per 1 µm:

m²/liter
 11.4

Note: *The practical material usage depends on many factors i.e. shape of the object, roughness of the surface, application techniques, pressure and application circumstances.*

VOC

2004/42/Ilb(e)(840)772

The EU limit value for this product (product category: Ilb(e)) in ready to use form is 840 gram/liter of VOC. The VOC content of this product in ready to use form is max. 772 gram/liter.

Product storage

Product shelf-life is determined when products are stored unopened at 20°C. Avoid extreme temperature fluctuation.

- Product shelf life data see TDS S9.01.02



1K All Plastics Primer

FOR PROFESSIONAL USE ONLY

AkzoNobel Car Refinish bv. [Change in local name; i.e. Coatings LTD / Inc.](#)
Address: [Rijksstraatweg 31, PO Box 3, 2170 BA Sassenheim \(change to local address\)](#)
Tel: [+31\(0\)71308-6944 \(Change to local phone number\)](#)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com

