


Autoclear Mix & Matt


FOR PROFESSIONAL USE ONLY

Description

Two-pack, matting finish for application over Autowave 2.0.
The desired gloss level can be achieved by mixing of the Low and Semi Gloss components.



100 Autoclear Mix & Matt
40 Autoclear Mix & Matt Hardener
60 Autoclear Mix & Matt Reducer




Use Sikkens measuring stick

43




Spray gun set-up:
1.3 – 1.4 mm

Application pressure:
1.7-2.2 bar at the air inlet
HVLP max 0.6-0.7 bar at the air cap



2 x 1 coat



Between coats
15 minutes at 20°C

Before curing
15 minutes at 20°C



Drying	20°C	60°C
Low Gloss	1 hour	15 minutes
Semi Gloss	1½ hour	20 minutes



Use suitable respiratory protection
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information

Autoclear Mix & Matt

FOR PROFESSIONAL USE ONLY

Description

Two-pack, matting finish for application over Autowave.
The desired gloss level can be achieved by mixing of the Low and Semi Gloss components.

Product and additives

Clearcoat	Autoclear Mix & Matt Low Gloss Autoclear Mix & Matt Semi Gloss
Hardener	Autoclear Mix & Matt Hardener
Reducer	Autoclear Mix & Matt Reducer Standard Autoclear Mix & Matt Reducer Slow

No plasticiser (Elast-O-Actif) required for application on plastic car parts.


Basic raw materials

Autoclear Mix & Matt:	Polyester resin
Autoclear Mix & Matt Hardener:	Poly-isocyanate resin

Suitable substrates

Autowave 2.0:
Sanded original finishes


Gloss level



	Gloss level	Low Gloss	Semi Gloss
M1	Low Gloss	100	0
M2		80	20
M3		50	50
M4		20	80
M5	Semi Gloss	0	100

All gloss levels between M1 and M5 can be achieved by mixing Low and Semi Gloss by weight (see table above). The gloss level is an impression and can be judged by the gloss level swatch but preferably by spray outs produced.

Mixing



By volume		By weight	
100	Autoclear Mix & Matt	100	Autoclear Mix & Matt
40	Autoclear Mix & Matt Hardener	42	Autoclear Mix & Matt Hardener
60	Autoclear Mix & Matt Reducer	55	Autoclear Mix & Matt Reducer

Use measuring stick No. 43

Note: Stir Autoclear Mix & Matt before use.


Note: Always use a paint strainer with a maximum mesh of 125 micron.

Note: Make sure to mask body apertures to avoid gloss differences.

Autoclear Mix & Matt

FOR PROFESSIONAL USE ONLY

Viscosity



17-19 seconds – DIN Cup 4 at 20°C

Spray gun set-up / application pressure



Spray gun
Gravity feed

Fluid tip – set-up
1.3-1.4 mm

Application pressure
1.7-2.2 bar at the spray gun air inlet
HVLP max 0.6-0.7 bar at the air cap

Application process



Apply 2 coats, allowing to flash-off until completely matt.

For horizontal parts, apply 1 coat and allow to flash off. Next apply a cross coat.


Note: This product is designed for total respray or edge to edge application.

Pot-life

1 hour at 20°C

Drying times

Allow to flash-off until completely matt.



		Autoclear Mix & Matt Low Gloss		Autoclear Mix & Matt Semi Gloss	
		Reducer Standard	Reducer Slow	Reducer Standard	Reducer Slow

20°C	Dust dry	15 min	25 min	20 min	30 min
	Dry to handle*	1 hour	2 hours	1½ hours	3 hours

50°C	Dust dry	5 min	10 min	5 min	15 min
	Dry to handle*	20 min	25 min	25 min	30 min

60°C	Dust dry	5 min	10 min	5 min	10 min
	Dry to handle*	15 min	20 min	20 min	25 min

Allow the Autoclear Mix & Matt to cool down to ambient temperature.

Autoclear Mix & Matt

FOR PROFESSIONAL USE ONLY

Drying times (continued)



Allow 15 minutes flash off prior to infra red curing.

2 minutes at low intensity + 6 minutes at high intensity.

The panel must not reach a temperature above 100°C while curing.
For additional infra red drying information; see TDS S9.01.01

Film thickness

By using the recommended application:

40-50 µm

Theoretical coverage

Ready for use mixture at 1 µm layer thickness:

Low Gloss

335 m²/liter

Semi Gloss

320 m²/liter

Cleaning of equipment

Sikkens Solvents or solvent borne guncleaners

VOC

2004/42/IIb(e)(840)620

The EU limit value for this product (product category: IIB.d) in ready to use form is max. 840 g/liter VOC.
The VOC content of this product in ready to use form is max. 620 g/liter.

Product storage

Product shelf-life is determined when products are stored unopened at 20°C.
Avoid extreme temperature fluctuation.
Product shelf life data see TDS S9.01.02

Maintenance

For cleaning and maintenance of matt finishes, see TDS S8.01.07

Akzo Nobel Coatings LTD

Address: Unit 2B, Didcot Park
Churchward, Southmead Industrial Estate
Didcot, Oxfordshire, OX11 7HB
Tel: +44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com