


Autoclear LV Superior


FOR PROFESSIONAL USE ONLY

Description

Two-pack VOC compliant clearcoat concept, consisting of three clearcoats, one dedicated hardener and three reducers, designed for optimum application properties. This concept covers all sizes of repairs at optimum quality levels under all application conditions. The clearcoat technology will ensure a very robust and reliable product performance combined with high gloss level.



100 Autoclear LV Superior Clearcoats
60 Autoclear LV Superior Hardener
20 Autoclear LV Superior Reducers




Use Sikkens measuring stick

31 Blue




Spray gun set-up:
1.2-1.4 mm

Application pressure:
1.7-2.2 bar at the air inlet
HVLP max 0.6-0.7 bar at the air cap




2 x 1 coat
First apply a medium closed coat, next apply a full coat



Between coats
3-5 minutes at 20°C

Before curing
3-5 minutes at 20°C



Autoclear LV Superior Fast
Autoclear LV Superior Medium
Autoclear LV Superior Slow

	20°C	60°C
Autoclear LV Superior Fast	6 hours	15 minutes
Autoclear LV Superior Medium	7 hours	25 minutes
Autoclear LV Superior Slow	8 hours	35 minutes



Use suitable respiratory protection
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information

Autoclear LV Superior

FOR PROFESSIONAL USE ONLY

Description

Two-pack VOC compliant clearcoat concept, consisting of three clearcoats, one dedicated hardener and three reducers, designed for optimum application properties. This concept covers all sizes of repairs at optimum quality levels under all application conditions. The clearcoat technology will ensure a very robust and reliable product performance combined with high gloss level.

Product and additives

Autoclear LV Superior Fast:	15 minutes drying time at 60°C
Autoclear LV Superior Medium:	25 minutes drying time at 60°C
Autoclear LV Superior Slow:	35 minutes drying time at 60°C

Hardener Autoclear LV Superior Hardener

Reducers Autoclear LV Superior Reducer Fast: spot and panel repairs below 20°C
Autoclear LV Superior Reducer Medium: spot and panel repairs (20°C-35°C)
Autoclear LV Superior Reducer Slow: larger areas and overall refinishing at (25°C-45°C)

Accelerator Autoclear LV Superior Accelerator: for spot and panel repairs at temperatures **below 30°C**

Additives Autoclear Mat: See TDS 5.5.1


Basic raw materials

Autoclear LV Superior:	Polyol resins
Autoclear LV Superior Hardener:	Poly-isocyanate resins

Suitable substrates

Autowave
Autowave 2.0
Autobase Plus + 10% Hardener P25

Mixing




100 Autoclear LV Superior
60 Autoclear LV Superior Hardener
20 Autoclear LV Superior Reducer(s)

100 Autoclear LV Superior Fast/Medium
60 Autoclear LV Superior Hardener
20 Autoclear LV Superior Accelerator

Use measuring stick No. 31 Blue.

Viscosity



15-17 seconds DIN Cup 4 at 20°C.

Spray gun set-up / application pressure



Spray gun
Gravity feed

Fluid tip – set-up
1.2-1.4 mm

Application pressure
1.7-2.2 bar at the spray gun air inlet
HVLP max 0.6-0.7 bar at the air cap

Autoclear LV Superior

FOR PROFESSIONAL USE ONLY

Application process & blending



Apply a medium closed coat, allow for 3-5 minutes flash-off and apply a full coat.
Flash off 3-5 minutes before baking.

Recoat with itself within 24 hours
For blending, see TDS S8.01.01

Pot-life

Autoclear LV Superior Fast	30 minutes	at 20°C
Autoclear LV Superior Fast + Autoclear LV Superior Accelerator	30 minutes	at 20°C
Autoclear LV Superior Medium	1 hour	at 20°C
Autoclear LV Superior Medium + Autoclear LV Superior Accelerator	1 hour	at 20°C
Autoclear LV Superior Slow	1½ hour	at 20°C

Drying times

Allow for a minimum of 5 minutes flash off time at 20°C before moving the car into a pre-heated drying oven (booth) at 60°C. All drying times relate to standard application and object temperature.
Consider the time required for the spraybooth to reach an acceptable air temperature to enable the heat transfer of 60°C to the object.

		LV Superior Fast LV Superior Accelerator	LV Superior Medium LV Superior Accelerator	LV Superior Fast	LV Superior Medium	LV Superior Slow
20°C	Dust dry	50 minutes	50 minutes	1 hour	1 ½ hours	2 ½ hours
	Dry to handle*	3 hours	3 hours	6 hours	7 hours	8 hours
50°C	Dust dry	7 minutes	10 minutes	10 minutes	20 minutes	25 minutes
	Dry to handle*	20 minutes	25 minutes	30 minutes	50 minutes	60 minutes
60°C	Dust dry	4 minutes	6 minutes	7 minutes	10 minutes	20 minutes
	Dry to handle*	12 minutes	15 minutes	15 minutes	25 minutes	35 minutes

*Dry to handle

Following the drying cycle at 60°C object temperature, allow the Autoclear LV Superior to cool down fully to ambient temperature.




Allow 5 minutes flash off prior to infra red curing
The panel temperature should not exceed 100°C.
For additional information, see TDS S9.01.01

Autoclear LV Superior

FOR PROFESSIONAL USE ONLY

Polishability



Ready to polish after the stated air-dry times or 1 hour after cool down to ambient temperature

Film thickness

By using the recommended application (2 coats)

µm
45-60

Theoretical Coverage

Ready for use mixture at 1 µm layer thickness

± 510 m²/liter

Cleaning of equipment

Sikkens Solvent or solvent borne guncleaners

VOC

2004/42/IIb(d)(420)420

The EU limit value for this product (product category: IIb.d) in ready to use form is max. 420 g/liter VOC.
The VOC content of this product in ready to use form is max. 420 g/liter.

Product storage

Product shelf-life is determined when products are stored unopened at 20°C.
Avoid extreme temperature fluctuation.

- Product shelf life data see TDS S9.01.02

AkzoNobel Car Refinish bv.

Address: Rijksweg 31, PO Box 3, 2170 BA Sassenheim

Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com