

オートクリヤーWB SRA シンナー Autoclear WB SRA Thinner

用途

オートクリヤーWB SRA シンナーは、オートクリヤーWB のボカシ用シンナーで、スポット補修時のボカシ際ミストをなじませるために使用します。

使用できる製品

オートクリヤー WB

被塗物の前処理



クリヤーのボカシ際に付着している汚れを水と洗剤にて洗浄し、油分を脱脂洗浄にて十分に除去してください。




クリヤーのボカシ部分は 3M7448 スコッチブライトグレーに3M スカッフジェル 6013 を使用してスカフティング及びコンパウンドで磨いてください。

スプレー方法



Step 1 希釈済みのオートクリヤーWB に同量のオートクリヤーWB SRA シンナーを添加する。

Step 2 ライトコートでボカシ部分にスプレーする。



Step 3 次にボカシ部分をオートクリヤーWB SRA シンナー単体でスプレーする。



Step 4 必要であれば、約 10～15 秒のフラッシュオフタイム後にもう一度オートクリヤーWB SRA シンナーをスプレーする。

VOC 含有量

840g/L (理論上でのスプレーする塗料)

貯蔵安定期間

オートクリヤーWB SRA シンナー 20°C/1 年間

アクゾノーベル株式会社 自動車補修塗料事業部
東京都国立市泉 4 丁目 8 - 7
Tel :042 - 843 - 0081

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com