

M700 Anti Static Silicon Remover

M700 アンチスタティックシリコンリムーバー

FOR PROFESSIONAL USE ONLY

用途

M700 アンチスタティックシリコンリムーバーはアクリルラッカー塗膜を含む旧塗膜、すべてのシッケンズプライマー/サフェーサーの脱脂および清掃に適しています。また、ファイバーグラス類を含むプラスチック製品の静電気除去の効果も備えています。

静電気防止効果のため M 600 よりも蒸発が遅く設定されています。

ラッカー系のブラサフまたは塗装直後の完全乾燥していない塗膜に使用するには注意が必要です。

脱脂洗浄の前に

補修塗装作業を行う際に、先ず最初の工程として洗車を行なうようにしてください。温水と中性洗剤を用いて洗車を行なうことで水に溶けやすい付着物、例えば鳥糞、虫の死骸や樹液類などを除去することが出来ます。

使用方法

二枚の乾燥した清潔なウエスを使用し、一枚には脱脂剤をしみこませて被塗物表面を洗浄し、もう一枚のウエスで脱脂剤が蒸発（乾燥）する前に完全に拭き取ります。常に二枚のウエスで行なうようにしてください。一枚のみのウエスでは浮き上がった汚れを移動させているだけにすぎません。

表面清掃の目的は付着したグリース、オイル、ワックス、シリコーン、砂埃等を取り除くことにあります。正しい脱脂作業を行わないとサンディング後の研磨傷にグリース、オイル、ワックス、シリコーン等が入り込み、各ペイントシステムの剥離やブリスター等、不具合発生の可能性があります。

- 汚れたウエスは使用せず、常に清潔で新しいものを使用するようにしてください。使用したウエスは自然発火の恐れがあるために必ず密閉できる容器で保管してください。
- 脱脂剤の付着したウエスは密閉できる容器内で十分に乾燥させてから廃棄処分してください。

注意点

ブリスター発生の防止：

脱脂洗浄後は素手で塗装表面に触れないで下さい。手から出る汗や皮脂分が塗膜の剥がれやブリスター等の不具合を引き起こす可能性があります。また、保護クリームなどのついた手でも触れないように注意してください。

炭化水素系の脱脂剤（例えば M600, M700 アンチスタティックシリコンリムーバー等）は同じく有機系の汚れ（油脂分、グリースなどが付着した手で触れた汚れ）を取り除くのに効果的ですが、指紋などの汚れは水系の洗浄剤（M850）で取り除いてください。

やむを得ず脱脂洗浄後の被塗物を再度素手で触らなければならない場合は、もう一度脱脂洗浄作業を行ってください。その場合、炭化水素系及び水系の両脱脂剤を再度使用してください。

結露防止：

脱脂剤を使用すると、気化熱により金属表面の温度が下がり若干の結露を生じる場合があります。

密着不良やブリスターの発生を防ぐため、塗装を開始する前に必ず結露（水分）の付着が無いこと確認してから作業を開始してください。

車両を気温の低い場所（屋外）から高い場所（屋内）へ移動した際も同様の現象が発生する可能性があります。その場合は塗装までに 1 時間程度放置する必要があります。



M700 Anti Static Silicon Remover

M700 アンチスタティックシリコンリムーバー

FOR PROFESSIONAL USE ONLY

安全衛生



適切な安全保護具を使用してください。

アクゾノーベルコーティングではフレッシュエアーマスクの使用を推奨します。

VOC

780 g/L

製品の保管

製品の貯蔵安定期間は、20℃で未開封の場合を基準としています。

極端な温度変化を避けて保管してください。

※ 貯蔵安定期間については TDS S9.01.02 を参照して下さい。

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com

