


# Washprimer 1K CF

**FOR PROFESSIONAL USE ONLY**


## Description

A quick drying, universal one-pack Washprimer, suitable for direct use on bare metal and substrates.  
For use in the car refinishing market / industry, mainly designed for spot priming of sanded through bare metal areas.  
Washprimer 1K CF provides excellent adhesion and corrosion resistance of the paint systems subsequently applied.



100 Washprimer 1K CF

50 Plus Reducers




Use Sikkens measuring stick

**1** Black




Spray gun set-up:  
1.2-1.6 mm

Application pressure:  
1.7-2.2 bar at the air inlet  
HVLP max (0.6-0.7 bar) at the air cap




1-2 x 1 coat



Recoat after:  
15 minutes at 20°C

Recoat within:  
24 hours at 20°C



Recoat with all Sikkens primers and fillers

With the exception of Autosurfacer UV, Primer Surfacer EP II, 2K polyester bodyfiller, Polysurfacer.



Use suitable respiratory protection  
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information

# Washprimer 1K CF

FOR PROFESSIONAL USE ONLY

## Description

A quick drying, universal one-pack Washprimer, suitable for direct use on bare metal and substrates.  
For use in the car refinishing market / industry, mainly designed for spot priming of sanded through bare metal areas.  
Washprimer 1K CF provides excellent adhesion and corrosion resistance of the paint systems subsequently applied.

## Suitable substrates

Steel  
Zinc-coated steel

Aluminum  
Stainless steel

## Products and additives

Washprimer 1K CF  
Plus Reducers

## Basic raw materials

Washprimer 1K CF: Polyvinyl butyral resins

## Surface preparation



Remove contamination using an appropriate cleaner.




Final sanding step P180 - P320  
*See TDS S8.06.02 for sanding specifications*



Remove contamination using an appropriate cleaner.


*Where bodyfiller is exposed, avoid contact with water (e.g. waterborne degreaser).*

## Mixing



- 100** Washprimer 1K CF  
**50** Plus Reducers
- Stir the Washprimer 1K CF thoroughly before adding Reducer.
  - Use mixing stick no 1

## Viscosity



16-18 seconds - DIN cup 4 at 20°C

# Washprimer 1K CF

**FOR PROFESSIONAL USE ONLY**

## Pot-life

6 months at 70°F (20°C)

## Spray gun set-up / application pressure




**Spray gun**  
Gravity feed


**Fluid tip – set-up**  
1.2-1.6 mm

**Application pressure**  
1.7-2.2 bar at the spray gun air inlet  
HVLP max 0.6-0.7 bar at the air cap

## Application



1-2 x 1 coat over bare metal substrates.  
Recommended application temperature between 15°C-35°C.  
Maximum relative humidity during application: 75%.




Allow for a 4-8 minutes flash off time between coats at 20°C.

## Film thickness


By using the recommended application: 6-12µm

## Recoat time



Allow for a minimum of 15 minutes flash off time at 20° C before recoating.  
Recoat within 24 hours at 20°C.

## Recoatable with



All Sikkens primers and fillers.  
With the exception of following products;  

- Any 2K polyester bodyfiller
- Sikkens Polysurfacer– Primer Surfacer EP II
- Sikkens basecoats

## Material usage

By using the recommended application, the theoretical material usage is ± 54 sq.ft.liter (5 m<sup>2</sup>/liter) RTS mixture.

*The practical material usage depends on many factors i.e. shape of the object, roughness of the surface, application techniques, pressure and application circumstances.*

## Cleaning of equipment

Sikkens Solvents or solvent borne Guncleaners

# Washprimer 1K CF

FOR PROFESSIONAL USE ONLY

## VOC

The EU limit value for this product (product category: IIB.c) in ready to use form is; 780 g/liter of VOC.  
The VOC content of this product in ready to use form is max. 760 g/liter.

## Product storage

Product shelf-life is determined when products are stored unopened at 20°C.  
Avoid extreme temperature fluctuation.

- *Product shelf life data see TDS S9.01.02*

### Akzo Nobel Coatings LTD

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** +44 (0)1235 862226

## FOR PROFESSIONAL USE ONLY

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

### Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.sikkenscr.com](http://www.sikkenscr.com)