


Autoclear LV


FOR PROFESSIONAL USE ONLY

Description

Autoclear LV and Autoclear LV Slow are a two-component VOC compliant clearcoat with one dedicated hardener and reducer resulting in a simple mixing ratio. The Autoclear LV Slow is recommended to use from 30°C upwards. The application window of the Autoclear LV and Autoclear LV Slow covers all sizes of repairs in the Car Refinishing and has been designed for application on the Autowave basecoat.



100 Autoclear LV (Slow)
50 Autoclear LV Hardener
10 Autoclear LV Reducer




Use Sikkens measuring stick

3 Purple




Spray gun set-up:
1.2-1.4 mm

Application pressure:
1.7-2.2 bar at the air inlet
HVLP max 0.6-0.7 bar at the air cap




2 x 1 coat
First apply a medium closed coat, next apply a full coat



Between coats
5-10 minutes at 20°C

Before curing
5-10 minutes at 20°C



	20°C	60°C
Autoclear LV	1 ½ hour	20 minutes
Autoclear LV Slow	4 hours	30 minutes



Use suitable respiratory protection
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information

Autoclear LV

FOR PROFESSIONAL USE ONLY

Description

Autoclear LV and Autoclear LV Slow are a two-component VOC compliant clearcoat with one dedicated hardener and reducer resulting in a simple mixing ratio. The Autoclear LV Slow is recommended to use from 30°C upwards. The application window of the Autoclear LV and Autoclear LV Slow covers all sizes of repairs in the Car Refinishing and has been designed for application on the Autowave basecoat.

Product and additives

Clearcoat	Autoclear LV: Autoclear LV Slow:	standard clearcoat for all repair sizes, to be used at temperatures up to 30°C. clearcoat to be used at higher temperatures and larger object sizes.
Hardener	Autoclear LV Hardener	
Reducer	Autoclear LV Reducer	
Additives	Autoclear Mat:	See TDS 5.1.1


Basic raw materials

Autoclear LV (Slow):	Polyol resins
Autoclear LV Hardener:	Poly-isocyanate resins

Suitable substrates

Autowave
Autowave 2.0

Mixing




100 Autoclear LV
50 Autoclear LV Hardener
10 Autoclear LV Reducer

Use measuring stick No. 3 Purple

100 Autoclear LV Slow
50 Autoclear LV Hardener
10 Autoclear LV Reducer

Viscosity



15-18 seconds DIN Cup 4 at 20°C.

Spray gun set-up / application pressure



Spray gun
Gravity feed


Fluid tip – set-up
1.2-1.4 mm

Application pressure
1.7-2.2 bar at the spray gun air inlet
HVLP max 0.6-0.7 bar at the air cap

Autoclear LV

FOR PROFESSIONAL USE ONLY

Application process & blending



Apply a medium closed coat, allow for 5-10 minutes flash-off and apply a full coat.
Flash off 5-10 minutes before baking.


Recoat with itself within 24 hours
For blending, see TDS S8.01.01.

Pot-life

Autoclear LV	30 minutes	at 20°C
Autoclear LV Slow	45 minutes	at 20°C

Drying times

Allow for a minimum of 5 minutes flash-off time at 20°C before moving the car into a pre-heated drying oven (booth) at 60°C. All drying times relate to standard application and object temperature.
Consider the time required for the spraybooth air temperature and object to reach 60°C.



Autoclear LV	Autoclear LV Slow
--------------	-------------------

20°C	Dust dry	45 minutes	60 minutes
	Dry to handle*	1 ½ hour	4 hours
50°C	Dust dry	15 minutes	30 minutes
	Dry to handle*	30 minutes	45 minutes
60°C	Dust dry	10 minutes	20 minutes
	Dry to handle*	20 minutes	30 minutes

*Dry to handle

Following the drying cycle at 60°C object temperature, allow the Autoclear LV (Slow) to cool down fully to ambient temperature.




Allow 5 minutes flash off prior to infra red curing
The panel temperature should not exceed 100°C.
For additional information, see TDS S9.01.01

Autoclear LV

FOR PROFESSIONAL USE ONLY

Polishability



Ready to polish after the stated air-dry times or 1 hour after cool down to ambient temperature.

Film thickness

By using the recommended application:

µm
45-60

Theoretical coverage

Ready for use mixture at 1 µm layer thickness:

522 m²/liter

Cleaning of equipment

Sikkens Solvent or solvent borne guncleaners

VOC

The EU limit value for this product (product category: IIB.d) in ready to use form is max. 420 g/liter VOC.
The VOC content of this product in ready to use form is max. 420 g/liter.

Product storage

Product shelf-life is determined when products are stored unopened at 20°C.
Avoid extreme temperature fluctuation.

- *Product shelf life data see TDS S9.01.02*

Akzo Nobel Car Refinish bv.

Address: Rijksweg 31, PO Box 3, 2170 BA Sassenheim

Tel: +31(0)71308-6944

FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com