

塗料粘度カップ換算表

概要

DIN cup No.4 と各種塗料粘度カップの換算表です。単位は 20°C/秒。

一覧表

DIN No.4	IWATA	FORD No.4	BS No.4	BS ISO No.4
14	11	13	17	23
15	13	14	18	27
16	15	16	20	32
17	16	17	23	36
18	17	18	25	41
19	18	20	27	45
20	20	21	28	49
21	22	23	30	54
22	23	24	32	57
23	25	26	34	61
24	26	28	36	66
25	27	29	38	72
26	28	31	40	74
27	31	32	42	78

アクゾノーベル株式会社 自動車補修塗料事業部
東京都国立市泉 4 丁目 8 - 7
Tel :042 - 843 - 0081

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com