

乾燥機器別の乾燥時間一覧表

概要

シッケンズ製品は、使用する乾燥機器のタイプにより乾燥方法及び乾燥時間を調節してください。

一覧表

製品名	機種	短波(6KW)				中波(17KW)			
		フラッシュオフ	距離	乾燥時間	機器セット	フラッシュオフ	距離	乾燥時間	機器セット
ポリキット IV		—	50-70	4-5	L	—	40-60	6-8	L
プライマーサフェーサー EP		5	50-70	5+10	L+H	5	40-60	5+12	L+H
サフェーサー類		5	50-70	4+8	L+H	5	40-60	6+10	L+H
オートクリヤー類		5	50-70	4+8	L+H	5	40-60	4+10	L+H
オートクリル プラス		5	50-70	6+6	L+H	5	40-60	4+8	L+H

製品名	機種	セラミック長波(4KW)				IR		
		フラッシュオフ	距離	乾燥時間	機器セット	フラッシュオフ	距離	プログラム No.
ポリキット IV		—	30-50	10	—	40-60	2	
オートクリル プラス		5	30-50	20	—	40-60	9	

フラッシュオフタイム = 分

距離の単位 = cm

乾燥時間 = 分

機器セット L = 低温乾燥

機器セット H = 高温乾燥

備考

- 短波及び中波を使用する際、ライト系とダーク系の塗色では乾燥温度が異なります。上記乾燥時間のデータは、それらの平均値になっています。
- 長波の乾燥時間には、乾燥温度の立ち上がり時間は含まれていません。
- 乾燥機のタイプにより、多少使用方法が異なる場合があります。詳細については、使用する乾燥機メーカーにお問い合わせください。

アクゾノーベル株式会社 自動車補修塗料事業部
東京都国立市泉4丁目8-7
Tel :042 - 843 - 0081

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com