

Polishing advice Autoclear LV Exclusive

FOR PROFESSIONAL USE ONLY

Description

Autoclear LV Exclusive has special reflow properties. For the perfect end result it is advised to polish after 12 hours. When polishing at the same day, it is important to use below mentioned polishing procedure.

Polishing advice

Do not polish within the first two hours after cooling down.

Flattening



P1200 Sand with 3M 260L P1200 with interface pad

P3000 Abrade with Trizact P3000 with interface pad (wet)

Polishing



Farecla:

1. Use Farecla G3 Premium with Farecla compound pad with soft back pad
2. Use Farecla G3 Glaze with black foam pad with soft back pad.
3. Wipe off polished area with a Farecla yellow polishing cloth

3M:

1. Use 3M Fast Cut Plus (Green Top) Compound with green pad
2. Use 3M Extra Fine Compound (Yellow Top) with yellow pad.
3. Wipe off polished area with a 3M yellow polishing cloth

Akzo Nobel Coatings LTD

Address: Unit 2B, Didcot Park
 Churchward, Southmead Industrial Estate
 Didcot, Oxfordshire, OX11 7HB
Tel: +44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. www.sikkenscr.com