

# Autowave<sup>®</sup> MM Optima SE8SA Toners

FOR PROFESSIONAL USE ONLY

## Description


The Autowave MM Optima is a comprehensive waterborne basecoat application system known for its excellent hiding properties. Autowave Optima MM must be used in conjunction with a specified Sikkens clearcoat to provide protection from the environment. This Technical Bulletin has been produced to give additional advice on application of colors containing SE8SA.



Gently shake the Autowave MM Optima SE8SA toners prior to use  
 Stir color formula before adding Autowave Optima WB Activator

### NOTE:

### Application for Toner SE8SA only



100 Autowave MM Optima  
 0-30 Activator Optima WB Activators



Use Sikkens measuring stick


**14** Blue



Spray gun set-up:

1.2-1.3  
 1.4 (Application in HT/LH conditions)

Application pressure @ spray gun air inlet:  
 1.7-2.2 bar (25-29psi)  
 HVLP max at air cap 0.6-0.7 (10psi)




Application:

2 x 1 coats

Application mist coat:


1 x 1 mist coat

No flash-off between coats  
 Flash-off until matt prior to mist coat



Prior to clearcoat application:

Until completely matt and dry



Clearcoat application  
 See clearcoat T.D.S.



Use suitable respiratory protection  
 Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete Autowave MM Optima TDS for detailed product information

# Autowave<sup>®</sup> MM Optima SE8SA Toners

FOR PROFESSIONAL USE ONLY

## Akzo Nobel Coatings LTD

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** +44 (0)1235 862226

### FOR PROFESSIONAL USE WITH SUITABLE HS&E EQUIPMENT

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coating brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

#### Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.sikkenscr.com](http://www.sikkenscr.com)