

Hail Damage Repair

FOR PROFESSIONAL USE ONLY

Description


This Bulletin describes the optimum repair system for substrate damages caused by hail.

Process Steps

Dent removal should be executed to such an extent that the maximum film build of body filler does not exceed 500 µm. Polysurfacer application should not be over 300 µm.



Remove surface contamination using the appropriate surface cleaner. Next, clean the surface with warm water and detergent, rinse sufficiently with clean water.



P80/P120 Remove the existing finish.
 P220 Sand a larger featheredge with P220 grit.



Remove surface contamination using the appropriate surface cleaner.



Apply a single coat of Primer Surfacer EP

Important:

- Apply a maximum layer thickness of 25 µm.
- To avoid lifting do not apply Primer Surfacer EP too wet. See TDS S2.04.3



Recommended:
 5 minutes low power 10 minutes high power 50-70 cm distance

Allow 5 minutes flash-off prior to infra red curing
 Temperature should not exceed 100°C.



Optional:
 45 minutes at 60°C or 16 hours at 20°C



P220-P320 Abrade the Primer Surfacer EP.
 ➤ Do not sand through the Primer Surfacer EP.
 ➤ Apply the appropriate polyester bodyfiller or Polysurfacer

Important: In case of using Polysurfacer, first apply a thin coat to avoid lifting and flash off for at least 5 minutes, before applying the next coat. See TDS S3.05.01

Hail Damage Repair

FOR PROFESSIONAL USE ONLY

Process steps (continued)

After drying, sand the polyester bodyfiller or Polysurfacer with P120-P220 grit.

Important:

- After sanding, the maximum film build of body filler should not exceed 500 µm.
- Polysurfacer application should not be over 300 µm.



Important: Sikkens Polysurfacer should not be applied to bare metal.

Therefore it is advised to proceed with a single coat of Primer Surfacer EP and dry as described before.

Apply Primer Surfacer EP



Note: It is advised when Autowave 2.0 is used as a topcoat it should be preceded with Colorbuild Plus Primer Surfacer Sanding or Non Sanding.

Recommended:

15 minutes Low power, 50 – 70 cm distance.
 Temperature should not exceed 90°C.




Optional:

45 minutes at 60°C or 16 hours at 20°C



After drying sand the Primer Surfacer EP with P320-P400/P500 grit.



Remove surface contamination using the appropriate surface cleaner



Apply required topcoat according to the respective TDS



Hail Damage Repair

FOR PROFESSIONAL USE ONLY

AkzoNobel Car Refinishes Australia Pty Ltd
Address: 269 Williamstown Road, Port Melbourne, VICTORIA, 3207
Tel: +61 3 9644 1711

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. <https://sikkensvr.com/au/>